

WHAT IS CLAIMED IS;

1. A manufacturing method of a polarizing film comprising steps of;  
laminating a protective film (B) onto at least one face of a polarizer (A),  
and thermocompression bonding.
2. The manufacturing method of the polarizing film according to Claim 1, wherein a heating treatment is performed from a side of the protective film (B).
3. The manufacturing method of the polarizing film according to Claim 1, wherein a heating treatment period of time is not more than five seconds.
4. The manufacturing method of the polarizing film according to Claim 1, wherein a heating treatment temperature is not less than 90 °C.
5. The manufacturing method of the polarizing film according to Claim 1, wherein a pressurization is performed by applying a linear loads pressure at not less than 5 N/cm.
6. The manufacturing method of the polarizing film according to Claim 1, wherein thermocompression bonding is performed by applying a heating treatment and a pressurization simultaneously.
7. A polarizing film obtained by the manufacturing method according to Claim 1.
8. An optical film in which at least one polarizing film

according to Claim 7 is laminated.

9. A visual display in which the polarizing film according to Claim 7 or the optical film according to Claim 8 is used.

206040-25295001